

## 310 Mo

**CATEGORIE** SMAW beklede elektroden

**TYPE** Heat resistant (modified) stainless steel alloy for SMAW

**APPLICATIONS** Ceweld 310Mo electrodes are primarily intended for welding the clad side of 316, 316L and 317 clad steels as well as other grades of molybdenum bearing stainless steels. Ceweld 310Mo electrodes are used for the resurfacing of digesters in the paper industry

**PROPERTIES** Ceweld 310Mo is a rutile basic electrode similar to Ceweld 4842 Ti but with molybdenum added for improved high temperature creep properties. The weld deposit is fully austenitic and corrosion resistant.

**CLASSIFICATION**

AWS	A 5.4: E 310 Mo-16
EN ISO	3581-A: E 25 20 3 R 12
DIN: W.Nr.	1.4466
DIN	8556: E 25 22 2 NLB

**SUITABLE FOR** 1.4832, 1.4837, 1.4841, 1.4845, 1.4846, 1.4849, 1.4848, 1.4828, 1.4713, 1.4726, 1.4710, 1.4745, 1.4823 heat resisting stainless steel.

**APPROVALS** CE approved

**WELDING POSITIONS:**



**WELD DEPOSIT ANALYSIS**

C	Mn	Si	Cr	Ni	Mo
<0.10	1,5-2.0	0.5	22-24	19-21	2-3

**MECHANICAL PROPERTIES**

Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness HV 40
				+20°C	-40°C	-60°C	
AW	380	540	35	70			210

AW: as welded

**WELDING PARAMETERS / PACKING**

Welding Parameters			Packing		
D (mm)	Length (mm)	Current (A) DC+	kg / can	kg / 6pack	kg / 1000
2,5	300	60-90			19
3.2	350	75-120			35.8
4.0	350	100-155			54.5
5.0	350	130-210			84.7

**REDRYING TEMPERATURE** 300°C/2hr (not often required)