

## AA Nicro 625B

**CATEGORIE** FCAW gevulde draad

**TYPE** Basic flux-cored nickel base welding wire for gas shielded arc welding.

**APPLICATIONS** AA Nicro 625B is developed for welding and cladding nickel-based alloys such as alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels or to stainless steels and for joining 6% molybdenum super austenitic steels.

**PROPERTIES** Latest generation basic slag guarantees optimum metallurgical quality and attractive welder appeal. The weld deposit meets the NiCrMo-3 requirements.  
Better bead aspect and shape compare to solid wires with better arc stability and improved wetting properties with less spatters.

**CLASSIFICATION**

AWS	A 5.34: E NiCrMo-3T0-4
EN ISO	14172: ~Typ Ni 6625 (NiCr22Mo9Nb)
DIN: W.Nr.	2.4321

**SUITABLE FOR** AA 625B is developed for welding and cladding nickel-based alloys such as alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels, to stainless steels and for joining 9% Nickel steels., X10NiCrAlTi, 32-20H, 32-21, X8 Ni9, ASTM A 533 Gr1, 800H, Sanicro 28, 254SMo, inconel 625, UNS : N08926, N08825, N06625. DIN : X8Ni9, X1NiCrMoCuN25 20 6, X1NiCrMoCuN25 20 5, NiCr21Mo, NiCr22Mo9Nb W.Nr.: 1.4876, 1.5656, 1.4529, 2.4858, 2.4856, 1.4539, 1.4547

**APPROVALS** CE approved

**WELDING POSITIONS:**



**ALL-WELD METAL ANALYSES %**

C	Mn	Si	Cr	Ni	Mo	Nb	Fe
0.025	0.4	0.3	21.0	rem	9.0	3.4	0.40

**ALL WELD METAL PROPERTIES (TYPICAL)**

Heat Treatment	R <sub>p0,2</sub> (N/mm <sup>2</sup> )	R <sub>m</sub> (N/mm <sup>2</sup> )	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness HRc / HV
				-20°C	-40°C	-196°C	
AW	500	780	40			60	

AW: as welded

**WELDING PARAMETERS / PACKING**

D (mm)	Welding Parameters			Packing		
	Voltage (V)	Current (A)	spool type	kg / spool	kg / pallet	
1.2	26-32	125-225	S-300	15	1080	
1.6	27-34	150-260	S-300	15	1080	

**REDRYING TEMPERATURE** 150°C / 24hr

**GAS ACC. EN ISO 14175:** M21